



Brushcrete

Acrylic Polymer modified waterproofing coating for concrete & masonry

Uses

Brushcrete polymer in conjunction with cement provides a seamless waterproof coating to concrete and masonry surfaces. It can be used as a waterproof or protective coating.

Advantages

- Can be applied in uniform thickness to horizontal and vertical surfaces.
- Develops excellent bond to most building materials.
- Reduces or prevents salt penetration into concrete.
- Is not affected by ultraviolet light or by chemicals ranging from mild acids to strong alkalies.
- Is highly durable in continuous wet condition.
- Is non-flammable and does not give off toxic gases, when exposed to fire.
- Non toxic

Description :

Brushcrete is a single component acrylic polymer which in conjunction with cement forms a composite polymer modified cementitious waterproofing system.

Technical Support

The company provides a technical advisory service supported by a team of specialists in the field.

Properties :

Pot life	:	20-30 min. at 30°C
Mixed Density of brushcrete topping	:	2.1-2.2 g/cc.
Colour	:	White liquid
Application temperature	:	> 10°C <35°C
Bond strength with concrete	:	≥ 1N/mm ²

Areas of Application :

- Waterproofing of toilets, terraces, roofs, etc.
- General concrete repairs
- Protection of concrete against salt attack etc.

Application Instructions

Surface Preparation

Prior to application of Brushcrete, surface must be prepared

as mentioned below to avoid failure :

The surface shall be cleaned to remove all dust, foreign matters, loose materials or any deposits of contamination which could affect the bond between the surface and the coating. This can be done by scarifying, grinding, water blasting, sand blasting, acid washing or by any other approved method.

New flat surface like sub-base concrete shall be made reasonably smooth so as not to impede the application of Brushcrete coating and to avoid sharp projections.

All concrete surfaces shall be thoroughly pre-wetted for at least one hour prior to the application of Brushcrete coating by pouring water on flat surface or by vigorously spraying water on vertical/inclined surfaces. When placing Brushcrete coating, water should be removed so that surface is only damp. In no case there should be standing water or a shiny wet surface.

Depressions are filled and leveled using Brushcrete fillers. For filler, the mixing ratio is 1 kg cement:1.5 by silica sand and 0.52 kg Brushcrete.

Mixing

Brushcrete Polymer is mixed with neat cement in the ratio of 100 kg cement:50 kg of Brushcrete. The mix has to be stirred thoroughly until no air bubbles remain in the mix. Any lump found in the mix should be removed.

Application :

The mix has to be applied by brush on rendered and/or prepared surface. Two or more coats are recommended. First coat should be allowed to stir dry for 5-6 hours. The surface should be made wet before application in case of porous structures.

Curing

During the first 12 hours of curing, it must be protected from abrasion, rain and other adverse conditions. No traffic shall be allowed on a Brushcrete treated surface within 48 hours after application. After application of final coat of Brushcrete, initial air drying shall be done for 2-6 hours. During this period no water is to be used for curing. In case of high temperature and low humidity combined with high wind condition, the coating shall be covered with polythene sheet to avoid rapid drying of the coating. After maximum period of 6 hours, the

Brushcrete

final application moist curing shall be done for the next 24 hours by way of spraying water on Brushcrete coating. During this period at no point of time should the Brushcrete coating be left completely dry or submerged in water. Following moist curing, the Brushcrete coating shall be allowed to air dry for 3 days before submersion in water if required for use

Cleaning

Brushcrete should be removed from tools and equipment immediately after use with clean water. Hardened material can be removed mechanically.

Estimating

Packaging

Brushcrete is supplied as a package of 10 L & 20 L container.

Yield/Coverage

Brushcrete Coating/Slurry

Mix Proportion : 100 kg cement : 50 kg Brushcrete

Material	1 coat on concrete Kg/m ²	2 coats on concrete Kg/m ²
Cement	0.50	0.75
Brushcrete	0.25	0.38

Brushcrete Topping

Mix Proportion : 100 kg cement : 50 kg Brushcrete

Material	Quantities of Material in Kg for	
	One cubic meter	1sq.m for 1.5mm thickness
Cement	860	1.30
Brushcrete polymer	440	0.70
Fine Silica Sand	860	1.30
Total Weight in kg	2160	3.30

Storage

Brushcrete has a shelf life of 12 months if unopened containers stored in cool dry place..

Precautions

Health and Safety instructions

Brushbond is non-toxic. Gloves and goggles should be worn. Any splashes to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, medical advice should be sought. Should use a dust mask while handling the powder.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

'Vishnu Chittam', No. 10, 2nd Floor
Sirur Park B Street, Seshadripuram
Bangalore 560020

www.fosroc.com

telephone

++91 80-2334 3188

fax

++91 80-2334 3178

e-mail

india@fosroc.com

Certified ISO 9001 by



Regional Offices

Bangalore

'Vishnu Chittam', No.10, 1stFloor
Sirur Park B Street, Seshadripuram
Bangalore 560 020
Ph:080-2334 3188
Fax : 080-23368667
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6411/12
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

109-113, 1st Floor, Vikrant Towers
4, Rajendra Place
New Delhi 110 008
Ph:011- 45062000-5
Fax: 011- 45062001
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bellary: 09845891690 ● Bhubaneswar : (0674) 2521176
- Chennai : (044) 24899949/24853383 ● Chandigarh : (0172) 2639360 ● Cochin : (0484) 2347465 ● Coimbatore : (0422) 2472966
- Goa : (0832) 09423058696 ● Guwahati : (0361) 2462866 ● Hyderabad : (040) 27662324/27662425 ● Indore : (0731) 4049339
- Jaipur : (0141) 2336103 ● Lucknow : (0522) 2239044 ● Nagpur: (0712) 2753510/2563242 ● Visakhapatnam : (0891) 2564850 / 2707607

INDIA/0863/A